

Final PCN

Lead Frame Supplier Source change to support the 32 VQFN component material

Dear Customer,

We are pleased to announce the successful completion of the qualification for the Lead Frame Supplier Mitsui High-tec Inc. (Fukuoka Japan) to support the 32 VQFN component material.

This document serves as the Final PCN notification for the use and migration to the 32 VQFN Lead Frame Supplier Mitsui High-tec Inc. (Fukuoka Japan). This described change is effective immediately based on the successful completion of the qualification to ensure continuity of supply without disruption.

Cirrus Logic would like to take this opportunity to thank our customers for their cooperation and assistance in this respective matter. Any specific or immediate inquiries should be directed to your local Field Sales Representative.

Sincerely,

Quality Systems Administrator Cirrus Logic Corporate Quality Phone: +1(512) 851-4000

Rev. 09062017A Cirrus Logic | 800 W. 6th St., Austin, TX 78701 | 512-851-4000 Page 1 of 4

CONFIDENTIAL



Products Affected:

The devices listed on this page are the complete list of affected devices. According to our records, these are the devices that you have purchased within the past twenty-four (24) months. The corresponding customer part number is also listed, if available.

Technical details of this Process / Product Change follow on the next page(s).

Title: Lead Frame Supp				plier Source change to support the 32 VQFN component material					
Customer Contact: Local Field Sales			s Representative Phone: (512) 851-		Phone: (512) 851-4	000	Dept: Corporate		orate Quality
Proposed 1 st Ship Date:			July	lly 2020 Estimated Sample Availability Date: June			June 2020		
	Assembly Site			Assembly Process			Assembly Materials		
	Wafer Fab Site			Wafer Fab Process			Wafer Fab Materials		
	Wafer Bump Site			Wafer Bump Process			Wafer Bump Material		
	Test Site			Test Process			Design		
	Electrical Specification		Χ	Mechanical Specification			Part Number		
	Packing/Shipping/Labeling		Χ	Other		Χ	Data Sheet		
Con	Comments: Lead Frame Mater			Supplier				•	

PCN Details


Description of Change:

- **Lead Frame Supplier:**
 - o From: Dynacraft Industries Sdn. Bhd. (Penang, Malaysia)
 - To: Mitsui High-tec Inc. (Fukuoka Japan)
 - Note: Mitsui High-tec Inc. is an existing Cirrus Logic qualified supplier
- Lead Frame POD (Package Outline Drawing) Dimension(s): (Reference Appendix A: Dimensional Comparison Drawing) (POD Remains Consistent with JEDEC Standard)

		CURRENT			NEW		
	Dim	Min	Nom	Max	Min	Nom	Max
pkg height	Α	0.85	0.9	0.95	0.8	0.85	0.9
metal exposed X	D2	3.60	3.70	3.80	3.55	3.65	3.75
metal exposed Y	E2	3.60	3.70	3.80	3.55	3.65	3.75
foot length	L	0.35	0.40	0.45	0.30	0.35	0.40
gap: foot vs metal exposed	K	0.2				0.33	

Note: Data sheet package dimensions will be update accordingly

Pin 1 Corner Style Designation on Heat Sink:





Rev. 09062017A Cirrus Logic | 800 W. 6th St., Austin, TX 78701 | 512-851-4000 Page 2 of 4 **CONFIDENTIAL** www.cirrus.com



Special Note: Items Remaining the Same								
	Lead Frame Material: Remains the same: C194							
	Mold Compound Material: Remains the same: Hitachi CEL 9240							
	DIE Attach Material: Remains the same: Ablebond 8290							
Moisture Sensitivity Level (MSL): Remains the same: MSL 3								
Reason for Chan	ge:							
Maintain continu	ty of material supply.							
Anticipated Impa	ct on Form, Fit, Function, Quality o	or Reliability:						
No anticipated adverse impact to the quality and/or reliability of said product.								
Anticipated Impact on Material Declaration:								
 ✓ No Impact to the Material Declarations or Product Content reports are driven from production data and will be available following the production release. 								
Product Affected:								
During Comment and Device Devi								
Device	Cirrus Logic Part Number CS8422-CNZ	Device	Cirrus Logic Part Number CS53L21-DNZ					
1 2	CS8422-CNZ CS8422-CNZR	11 12	CS53L21-DNZ CS53L21-DNZR					
3	CS42L51-CNZ	13	CS4265-CNZ					

On the Logic I are Harrison	D01100	on ac Logio i ait itamboi
CS8422-CNZ	11	CS53L21-DNZ
CS8422-CNZR	12	CS53L21-DNZR
CS42L51-CNZ	13	CS4265-CNZ
CS42L51-CNZR	14	CS4265-CNZR
CS42L51-DNZ	15	CS4265-DNZ
CS42L51-DNZR	16	CS4265-DNZR
CS43L21-CNZ	17	CS547329-INZ
CS43L21-CNZR	18	CS547329-INZR
CS53L21-CNZ	19	CS547366-INZ
CS53L21-CNZR	20	CS547366-INZR
	CS8422-CNZ CS8422-CNZR CS42L51-CNZ CS42L51-CNZR CS42L51-DNZ CS42L51-DNZ CS42L51-DNZR CS43L21-CNZ CS43L21-CNZ CS53L21-CNZ	CS8422-CNZ 11 CS8422-CNZR 12 CS42L51-CNZ 13 CS42L51-CNZR 14 CS42L51-DNZ 15 CS42L51-DNZR 16 CS43L21-CNZ 17 CS43L21-CNZR 18 CS53L21-CNZ 19

Changes To Product Identification Resulting From This PCN:	
There are no changes to the production identification	

Rev. 09062017A Cirrus Logic | 800 W. 6th St., Austin, TX 78701 | 512-851-4000 Page 3 of 4 **CONFIDENTIAL** www.cirrus.com



The Qualification Plans are designed using JEDEC and other applicable industry standards. An overall summary of the Qualification results will be submitted upon completion.

Qualification Plan

CS4265-xNZ[R]/C1 Qualification: ☐ Plan ☐ Test Results						
Reliability Test	Standard	Conditions	Sample Size (PASS/FAIL)			
Pre-Conditioning	JEDEC J-STD-020A	MSL3 / 260°C (1 Lots)	22 / 0			
Die Shear Strength	MIL-STD-883 METHOD 2019		40 / 0			
WBS (Wire Bond Shear)	JESD22 B116	Paragraph 4 (Procedure) (# Lots)	40 / 0			
WBP (Wire Bond Pull)	MIL-STD-883 Method 2011	Paragraph 3 (Procedure) (# Lots)	40 / 0			
Plating Thickness		40 Units (10 units / Block)	40 / 0			
SD (Solderability)	JESD22 B102	245°C / 8 hr steam age before SD (1 Lots)	15 / 0			
PD (Physical Dimensions)	JESD22 B100 + B108	Package outline per JESD95 Cpk > 1.50 per JESD95 (1 Lots)	40 / 0			

Notes:

- Qualification tests "pass" on zero fails for each test
- CS4265-xNZ[R]/C1 serves as the Qualification Vehicle for the 32 VQFN Lead Frame Material

Reliability Qualification Results:

The material has met all qualification requirements and is fit for use

Rev. 09062017A Cirrus Logic | 800 W. 6th St., Austin, TX 78701 | 512-851-4000 Page 4 of 4