

SKU: FLS80-4G TECHNICAL DATASHEET

SRA #80 Solvent-Based, Water-Soluble, Wave Flux



Key Features

- > Excellent for Copper and difficult-to-solder metals including Alloy 42, Alloy 51, and Nickel alloys
- > Effective on bare Copper, OSP, HASL, or plated surfaces
- > May be applied in either foam or spray systems
- > Solders single- and double-sided circuit boards
- Conforms to IPC ANSI J-STD-004, Type ORM1.

DESCRIPTION

SRA #80 Solvent-Based, Water-Soluble, Wave Flux is a high activity halide, Neutral organic acid (OA) foam flux formulated for difficult-to-solder surfaces where activated rosin fluxes and less active OA fluxes cannot be used. This flux combines a unique activation system with a special no-polyol base that is compatible with all solder masks, does not leave a post-solder white residue, and is an ideal choice for high volume soldering operations.

The solderability and cleanability of **SRA #80 Solvent-Based, Water-Soluble, Wave Flux**, along with excellent foaming characteristics and heat stability, provide a moderately low "solids" flux adaptable to a wide variety of board styles, sizes and thicknesses.

APPLICATION

WAVE SOLDERING

To ensure optimum flux activity, a topside temperature of 88-116°C/190-240°F is recommended. Residues from **SRA #80 Solvent-Based, Water-Soluble, Wave Flux** are completely water-soluble and can be removed in batch or in-line aqueous cleaning systems. For best cleaning results, wash residues immediately after soldering. A water temperature of 49-60°C/120-140°F is recommended for optimum results. However, excellent results are routinely achieved at lower water temperatures. The organic base of **SRA #80 Solvent-Based, Water-Soluble, Wave Flux** is non-toxic and low foaming. Rinse waters are completely biodegradable. Consult local authorities for disposal regulations.

Best results can be obtained by following these guidelines:

- Make certain that the PCB surfaces are free of any oil, grease, or other impurities.
- Maintain a consistent foam head by narrowing the flux chimney, or using dual flux stones.
- Add fresh flux to maintain proper flux level in flux tank.
- Replace flux daily if self-contained storage is not available. Otherwise, replace after every forty (40) hours of operation.
- Regularly clean the fluxing equipment. Never leave foaming stone in flux when pressure is not applied.
- Clean fluxing stone in flux thinner.
- Adjust the specific gravity to the nominal level with a hydrometer. Evaporated solvent should be replaced by the addition of flux thinner.



TECHNICAL DATASHEET



PHYSICAL PROPERTIES

Specific Gravity Density pH Color Solids Content Halide Content Flashpoint Recommended Topside Temperature Recommended Soldering Range **THIS PRODUCT IS RoHS COMPLIANT.** 0.848 ±□ 0.023 @ 25°C 6.95 lbs/Gallon @ 25°C 7.0-8.0 Clear liquid, pale yellow 17% 3.10% 53°F Tag Closed Cup Method 88-116°C/190-240°F 200-315°C/390-600°F

SAFETY PRECAUTIONS

SRA #80 Solvent-Based, Water-Soluble, Wave Flux is a flammable product and should be handled with care and the normal precautions taken when working with chemical products.

When soldering with **SRA #80 Solvent-Based, Water-Soluble, Wave Flux**, adequate exhaust ventilation should be provided. Avoid contact with eyes, skin, and mucous membranes. Always wear NIOSH approved safety equipment when working with chemicals. Store in plastic containers away from heat.

Refer to Material Safety Data Sheet (MSDS) for additional safety information.

SRA #80 Solvent-Based, Water-Soluble, Wave Flux has a two (2) year shelf life.

