



# **TG-A2200 Ultra Soft Thermal Pad**

REACH Compliant RoHS Compliant UL Compliant

#### **Features**

- · One side is non-sticky and easy to assemble
- · Ultra soft and good compressibility
- · Good insulation


## **Applications**

#### Best for high power applications

Electronic components - Electric Vehicles, 5G, Autopilot System, Mobile Phone, AIOT, HPC (High Performance Computing), Server, IC, CPU, MOS, LED, Mother Board, Power Supply, Heat Sink, LCD-TV, Notebook, PC, Telecom Device, Wireless Hub, DDR II Module, etc.

## **Properties**

### Thermal Resistance VS. Pressure VS. Deflection



Pressure(psi)	R(°C-in²/W)	Deflection(%)
10	1.460	38
30	1.390	50
50	1.300	52

30

40

80

Thermal Conductivity: 2.2 W/mK

0.8 1.2 1.4 1.6 1.7 1.8 2.2 3.2 3.6 4.0 4.5 5.0

Hardness: 15 (Shore 00) 25

20

Properties	TG-A2200	Unit	Tolerance	Test Method
Thermal Conductivity	2.2	W/mK	±10%	ASTM D5470
Thickness	0.5~2.0	mm	-	ASTM D374
	0.0197~0.0787	inch	-	ASTM D374
Color	Gray	-	-	Visual
Flame Rating	V-1	-	-	UL 94
Dielectric Breakdown Voltage	≥5	KV/mm	-	ASTM D149
Weight Loss	<1	%	-	ASTM E595
Density	2.7	g/cm³	±10%	ASTM D792
Working Temperature	-40~+180	°C	-	-
Volume Resistance	3×10 <sup>12</sup>	Ohm-m	-	ASTM D257
Elongation	55	%	-	ASTM D412
Standard Format	Sheets one	-	-	-
Hardness	15	Shore 00	±5	ASTM D2240

15

20

0

#### T-Global Technology (Europe & North America) Limited

10

t-Global

T-Global Technology are proud to announce the launch of a new company logo and mission statement as part of the ongoing growth and evolution of our company's brand.

Units 1-2 Cosford Business Park, Central Park, Lutterworth, Leicestershire, LE17 4QU, United Kingdom **E** sales@tglobaltechnology.com **T** +44 (0)1455 553 510 **W** www.tglobaltechnology.com

NOTICE: The information contained herein is to the best of our knowledge true and accurate. Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. All specifications are subject to change without notice. The protective film and release paper does not affect the function of the product. If there is no special requirement, the default depends on T-Global. Since the varied conditions of potential use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part and users should make their own test to determine the suitability of our products in any specific situation. This product is sold without warranty either expressed or implied, of fitness for a particular purpose or otherwise, except that this product shall be of standard quality, and except to the extent otherwise stated in T-Global Technology's invoice, quotation, or order acknowledgment.

<sup>\*</sup>Different tolerances according to the selected thickness

<sup>%</sup>Pre-cut for different shapes